

| RAW MATERIAL SHEET | P534 | Updated    |
|--------------------|------|------------|
| Food contact       |      | 2021-09-17 |

Due to changing regulations, some characteristics of our materials may change. We invite you to request a regularly updated data sheet.

| SPECIFICATIONS            |                         |                       |  |
|---------------------------|-------------------------|-----------------------|--|
| SPECIFICATIONS            | VALUES                  | STANDARDS             |  |
| HARDNESS 5 SEC            | 69 shA                  | ISO 868               |  |
| DENSITY                   | 0.95                    | ASTM D792 - ISO 1183  |  |
| TENSILE STRENGTH AT BREAK | 6.5 MPa                 | ASTM D412 - ISO 37    |  |
| ELONGATION AT BREAK       | 470 %                   | ASTM D412 - ISO 37    |  |
| D.R.C. 22H / 70°C         | 32 %                    | ASTM D395 B - ISO 815 |  |
| OPERATING TEMPERATURE     | -50.0°C / 90.0°C        |                       |  |
| COLOUR                    | Natural white colorable |                       |  |

Prodene P534 is a thermoplastic elastomer rubber of PP-EPDM type.

It cannot be used with grease (for these applications : please contact our technical department).

Prodene P534 is 100% recyclable.

## REGULATORY CONFORMITY

Reach 1907/2006/CE - RoHS 2011/65/CE - VHU 2000/53/CE

#### **CHEMISTRY**

## **BUILDING / CSTB**

VOC: SNFA has realized a study on windows powder-coated aluminium QUALICOAT with TPE gaskets. The SNFA technical report, available on request, demonstrates that the TPE family is classified A+.

FIRE RESISTANCE

UL94 HB

UL94 HB width 1,1mm and 3mm all colours

## OTHER INFORMATION

# **FOOD CONTACT**

FDA

# **GUARANTEE LIMIT**

The information in this leaflet is the most accurate expression of our current knowledge. However, they are given for information only. In addition, the conditions of employment beyond our control, this information does not imply any guarantee on our part. Each user of the material shall ensure, by all available means (including testing of the finished product in its appropriate environment) the suitability of the material supplied for its particular application. Our company can not be held responsible for any problem due to improper or inappropriate use of its materials.

PRODEX - Parc industriel de Chartres - 32 avenue Louis Pasteur - 28630 GELLAINVILLE - Tel : +33 2 37 25 77 83 - Fax : +33 2 37 25 99 84 - Email : prodex@prodex-elastomeres.com https://www.prodex-elastomeres.com

25/07/2022 1 / 1