

RAW MATERIAL SHEET

2020-10-13

P050

Updated

Food contact foam

Due to changing regulations, some characteristics of our materials may change. We invite you to request a regularly updated data sheet.

SPECIFICATIONS		
SPECIFICATIONS	VALUES	STANDARDS
HARDNESS 5 SEC	15 shA	ISO 868
DENSITY	0.5	ISO 2781
OPERATING TEMPERATURE	-50.0°C / 75.0°C	
COLOUR	Natural white colorable	

Prodene P050 is a foamed thermoplastic elastomer rubber of SEBS type.

This quality offers a good resistance to atmospheric agents, to ageing, to UV and to usual products (excluding organic solvents, aromatic and vegetable oils).

REGULATORY CONFORMITY

Reach 1907/2006/CE - RoHS 2011/65/CE - DEEE 2012/19/CE - VHU 2000/53/CE

CHEMISTRY

BUILDING / CSTB

VOC : SNFA has realized a study on windows powder-coated aluminium QUALICOAT with TPE gaskets. The SNFA technical report, available on request, demonstrates that the TPE family is classified A+.

FIRE RESISTANCE

No		
OTHER INFORMATION		
OTHER INFORMATION		
nternal test of water absorption : dumping without pressure 240 hours in water. Temperature 21°C: Absorption rating : 0.3 %. Quick ageing test made by HEXPOL TPE. Grey scale according to ISO 105-A02. Spectrophotocolorimetry according EN ISO 4892-2:2006. Q-Sun Xe3HS illuminant D65, 10° Results : Duration Appearance Grey scale d E brightness iso 2813 : 20° 60° 85° 0 hrs : NA NA 0,1 1,1 0,4 1000 hrs : no bubbles no cracks no deformation 4/5 0,69 0,3 2,4 0,8 2000 hrs : no bubbles no cracks no deformation 4/5 2,21 0,2 2,3 0,7		
3000 hrs : on-surface cracks 4/5 0,51 0,2 1,4 1,1 Fest results on request Can be sticked with kit Loctite 406 + primer 770.		
FOOD CONTACT		

See EC 1935/2004 - EC 10/2011 food contact document

GUARANTEE LIMIT

The information in this leaflet is the most accurate expression of our current knowledge. However, they are given for information only. In addition, the conditions of employment beyond our control, this information does not imply any guarantee on our part. Each user of the material shall ensure, by all available means (including testing of the finished product in its appropriate environment) the suitability of the material supplied for its particular application. Our company can not be held responsible for any problem due to improper or inappropriate use of its materials.

PRODEX - Parc industriel de Chartres - 32 avenue Louis Pasteur - 28630 GELLAINVILLE - Tel : +33 2 37 25 77 83 - Fax : +33 2 37 25 99 84 - Email : prodex@prodex-elastomeres.com https://www.prodex-elastomeres.com